


| | | |
|---|--|--|
|  <p>15 rue des Frères Lumière – BP 136 78374 PLAISIR FRANCE Tél : 01.30.80.81.98 Fax : 01.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p> | <p>TECHNICAL</p> <p>DATA SHEET</p> | <p>Ref : TDS/ PR-25</p> <p>Page : 1/3</p> <p>Rev : 9 Date : 04/10</p> |
|---|--|--|

RED DYE PENETRANT PR-25



MANUFACTURER: Sherwin (USA) / NDT-Europa (NL)

DESCRIPTION / APPLICATION(S):

Type II, Method A (waterwashable) and Method C (solvent removable) red dye penetrant, Level 2 as per ISO 3452-2 standard. High sensitivity, easy to wash.

Rhodamine-free, Azo III A2 amine (diazo) free.

Red dye penetrant with two dyes “color perfect”.

Companion products: Cleaner: N120, cleaning rags N120, DR-62.
Remover: N106A, DR-60, cleaning rags N106A.
Non aqueous wet developer: D-100, R60, D-106.

SPECIFICATION(S) / STANDARD(S):

- Conforms to code(s) : ASME, RCC-M
standard(s): ISO 3452-2
specification(s): ASTM-E-1417
- This product complies with REACH regulation.

PHYSICO-CHEMICAL PROPERTIES:

- Aspect : purple-red liquid
- Flash point : > 60°C
- Low sulphur, fluorine, chlorine, bromine content
- Compatible with any metal and some synthetic materials.

PACKAGING / TRANSPORT / STORAGE:

.Packaging: 400mL (CO₂), 500mL (butane-propane) spraycans
1, 5, 10, 25L cans

60, 200L drums

.Transport / Handling: Refer to Material Safety Data Sheet (MSDS).

.Storage / Shelf life:

Keep away from moisture

Temperature range: 0°C à 50° C

Keep packaging closed after taking out some of the product

Can: 48 months

Spraycan: 60 months

INSTRUCTIONS:

Surface must be free of contaminants, **even inside flaws**. Use adequate methods to remove oxides, paints, oil, water, etc.

Prior to applying penetrant, wipe out with cleaner N120 and rags or cleaning rags N120.

Allow 2 minutes for complete evaporation.

Apply penetrant by any adequate means (spraying, brushing, flowing, dipping, etc.).

Dwell time:

20 minutes are recommended. Dwell time may be shortened down to 10 minutes when only large cracks are sought for, or extended up to several hours for tight cracks.

Excess of penetrant removal:

This is a delicate operation. Remove the excess penetrant from the surface, being careful not to remove the penetrant trapped in the defects.

Rinse under low pressure (50 to 200 kPa), with the nozzle of gun 30 to 40 cm from the part, during the shortest time possible, until the red background disappears. If you can't or don't want to use water, carry out the following procedure (and not any other).

- Wipe off the excess of penetrant from the surface using clean rags.
- Using rags lightly moistened with N106A or DR-60, wipe again.
- As a final step, wipe with clean, dry rags.

Developer:

After complete drying apply one of the mentioned developers as a thin, even coat by spraying only.

Wait for 10 to 30 minutes before inspection.

Inspection:

Parts shall be inspected as per ISO 3059 standard requirements.

Inspection is better when using a "cold" white light (industrial white light) or "intermediate" white light ("cool white" light). Colour temperature must be higher than 4500K. Colour rendition index more than 80 or light with an illuminating index of D65. It is recommended



15 rue des Frères Lumière – BP 136
78374 PLAISIR
FRANCE

Tél : 01.30.80.81.98

Fax : 01.30.80.81.99

WEB : www.babbco.fr

E-MAIL : sherwinbabbco@orange.fr

TECHNICAL

DATA SHEET

Ref : TDS/ **PR-25**

Page : 3/3

Rev : 9 Date : 04/10

NOT TO USE undervoltaged incandescent bulbs, as it often happens with battery-operated units, this giving a yellowish light.

HEALTH AND SAFETY: Refer to Material Safety Data Sheet (MSDS).

The information given herein is given in good faith to our customers for the sole purpose of assisting them in the use of the products. The document contains no formal or implicit guarantee regarding its use.

Babb Co cannot be held responsible for damages of any nature resulting from information provided in this document. In addition, none of the information which the document contains should be interpreted as a recommendation for the use of the products which would infringe the protected rights of industrial property.